



DOWEX™ MARATHON™ C

A Uniform Particle Size, High Capacity Cation Exchange Resin for Softening (Industrial and Residential) and Demineralization Applications

Product	Type	Matrix	Functional group
DOWEX™ MARATHON™ C	Strong acid cation	Styrene-DVB, gel	Sulfonic acid

Guaranteed Sales Specifications		Na ⁺ form	H ⁺ form
Total exchange capacity, min.	eq/L	2.0	1.8
	kgr/ft ³ as CaCO ₃	43.7	39.3
Water content	%	42 - 48	50 - 56
Uniformity coefficient, max.		1.1	1.1

Typical Physical and Chemical Properties		Na ⁺ form	H ⁺ form
Mean particle size†	μm	585 ± 50	600 ± 50
Whole uncracked beads	%	95 - 100	95 - 100
Total swelling (Na ⁺ → H ⁺)	%	8	8
Particle density	g/mL	1.28	1.20
Shipping weight	g/L	820	800
	lbs/ft ³	51	50

Recommended Operating Conditions	• Maximum operating temperature	120°C (250°F)
	• pH range	0 - 14
	• Bed depth, min.	800 mm (2.6 ft)
	• Flow rates:	
	Service/fast rinse	5 - 60 m/h (2 - 24 gpm/ft ²)
	Backwash	see figure 1
	Co-current regeneration/displacement rinse	1 - 10 m/h (0.4 - 4 gpm /ft ²)
	Counter-current regeneration/displacement rinse	5 - 20 m/h (2 - 8 gpm /ft ²)
• Total rinse requirement	2 - 5 Bed volumes	
• Regenerant	1 - 8% H ₂ SO ₄ , 4 - 8% HCl or 8 - 12% NaCl	

† For additional particle size information, please refer to Particle Size Distribution Cross Reference Chart (Form No. 177-01775).

Typical Properties and Applications

DOWEX™ MARATHON™ C strong acid cation exchange resin is a uniform particle size resin designed for industrial and residential softening and demineralization applications. The small uniform beads exhibit faster kinetics than conventionally sized resins. The improved kinetics results in improved regeneration efficiency, higher operating capacity, reduced regenerant usage and less waste water.

DOWEX MARATHON C resin also shows outstanding stability to compressive and osmotic stress.

Packaging

25 liter bags or 5 cubic feet fiber drums

Figure 1. Backwash Expansion Data





Figure 2. Pressure Drop Data



For other temperatures use:

$$F_T = F_{77°F} [1 + 0.008 (T_F - 77)], \text{ where } F \equiv \text{gpm/ft}^2$$

$$F_T = F_{25°C} [1 + 0.008 (1.8T_C - 45)], \text{ where } F \equiv \text{m/h}$$

For other temperatures use:

$$P_T = P_{20°C} / (0.026 T_C + 0.48), \text{ where } P \equiv \text{bar/m}$$

$$P_T = P_{68°F} / (0.014 T_F + 0.05), \text{ where } P \equiv \text{psi/ft}$$

Note: These resins may be subject to drinking water application restrictions in some countries: please check the application status before use and sale.

Warning: Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.

Notice: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

