



info@lenntech.com Tel. +31-152-610-900 www.lenntech.com Fax. +31-152-616-289

SeIRO® MPS-36 - pH Stable Membrane

Nanofiltration Spiral Module Series - 8040

PRODUCT DESCRIPTION

 Membrane Chemistry:
 Proprietary composite nanofiltration membrane

Membrane Type: pH stable nanofiltration membrane

Molecular Weight Cutoff (MWCO): 1000 Dalton

Construction: Spiral wound element Permeate Tube: Stainless steel

Major Applications:Acid and caustic recovery, product concentrationOptions:Feed channel spacers: 30 mil (X) and 57 mil (Z)

SPECIFICATIONS*	Model	Part Number	Rejection [%]		Permeate Flow	Membrane Area	Feed Spacer
01			Glucose /	NaCl	gpd (m³/day)	ft ² (m ²)	mil (mm)
			Sucrose				
	MPS-36 8040 B2>	0770116	30 / 50	10	34,500 (130)	290 (27)	30 (0.8)
	MPS-36 8040 B27	0770207	30 / 50	10	24,000 (91)	205 (19)	57 (1.4)
	*Test Conditions: RO w	ater at 440 psi (30	bar), 86°F (30°C)	. Feed solu	ution for rejection tests is	s 3% glucose / 3% sucros	e or 5% NaCl.

OPERATING AND DESIGN INFORMATION

Typical Operating Pressure: 220-510 psi (15-35 bar) **Maximum Temperature**: 158°F (70°C)**

Allowable pH - Continuous Operation: 1-13***
Allowable pH - Clean-In-Place (CIP): 1-13***


Maximum Pressure Drop Per Element: 10 psi (0.7 bar)
Maximum Pressure Drop Per Vessel (5 in Series): 50 psi (3.5 bar)

* Consult Process Technology group for specific applications.

Please refer to the Operating Envelope of Code 30 Membranes when temperature is higher than 122°F (50°C).

*** Corrosive acids should be avoided when a stainless steel permeate tube is being used.

NOMINAL DIMENSIONS



Model	Part Number	A	Α		В		С	
		inches	(mm)	inches	(mm)	inches	(mm)	
MPS-36 8040 B2X	0770116	40.0	(1016)	7.9	(200)	1.187	(30.15)	
MPS-36 8040 B2Z	0770207	40.0	(1016)	7.9	(200)	1.187	(30.15)	

Membrane Characteristics:

SelRO® Composite nanofiltration membrane in a spiral wound configuration, with superior pH and temperature stability.

Operating Limits:

- Operating Pressure: Maximum operating pressure for SelRO® MPS-36 is 510 psi (35 bar). Actual operating pressure is dependent upon system flux rate, as well as feed, recovery and temperature conditions.
- Permeate Pressure: Maximum allowed permeate pressure is 3 psi (0.2 bar).
- Differential Pressure: Maximum differential pressure limit is 10 psi (0.7 bar) per element. Maximum differential pressure for any length vessel is 50 psi (3.5 bar).
- Temperature: Maximum operating temperature is 158°F (70°C). For guidelines of recommended temperature and pressure please refer to the "Recommended Envelope for Code 30 Membranes" in this document.
- pH: Allowable range for continuous operation is 0-14. When a stainless steel permeate tube is used, corrosive acids should be avoided.
- Water Quality for Cleaning and Diafiltration:

Turbidity: Maximum feed turbidity is 1 NTU.

Guidelines: For more details please consult with KMS Process Technology Group.


• Chlorine and Chemical Exposure:

- It is not recommended to expose the MPS-36 membrane to chlorine or other oxidants, as it may affect the membrane performance.
- Sodium metabisulfite (without catalysts such as cobalt) is the preferred chemical to eliminate free chlorine or other oxidizers in the feed.
- It is not recommended to expose the MPS-36 membrane to organic solvents, such as alcohol, acetone, etc.
- Feed Flow Rate: Maximum and minimum flow rate for the MPS-36 spiral module are as follows:

Min. 25 gpm (95 liter/min) Max. 75 gpm (285 liter/min) Actual feed flow rate is dependent upon system flux rate, feed characteristics, fouling tendency and system design.

• Operating Envelope For Code 30 Membranes:

It is important to follow the pressure - temperature relationship guidelines, in order to prevent irreversible compaction and performance deterioration. The following diagram should be used as a guideline to operating the MPS-36 spiral module:



Element Handling:

 Recommended Cleaning Materials: Depending on the nature of the feed, the following cleaning agents can be chosen:

0.1-5% w/w sodium hydroxide at 122°F (50°C)

0.2-1% w/w nitric or phosphoric acid at 122°F (50°C)

0.1-0.5% w/w detergent mix KOCHKLEEN® KLD-III

0.5% anionic surfactant (such as SDS) at 122°F (50°C)

Consult KMS regarding the use of other cleaning materials.

- Lubricants: For element installation, use only water or glycerin
 to lubricate seals. The use of petroleum or vegetable-based oils
 or solvents may damage the element and will void any warranty.
- Storage Solution: Should be made with:

Short Term (up to two weeks): 0.25 w/w sodium metabisulfite. Long Term: 0.7% w/w benzalkonium chloride.

Glycerin should not be used for storage of the MPS-36 membrane.

The membrane module should not get dry. It should be stored in a sealed bag, in a temperature ranging from 36°F - 86°F (2°C - 30°C).

Service and Ongoing Technical Support:

Koch Membrane Systems (KMS) has an experienced staff of professionals available to assist end-users and OEM's for optimization of existing systems and support with the development of new applications. KMS also offers a complete line of KOCHKLEEN® membrane pretreatment, cleaning, and maintenance chemicals.

The information contained in this publication is believed to be accurate and reliable, but is not to be construed as implying any warranty or guarantee of performance. We assume no responsibility, obligation or liability for results obtained or damages incurred through the application of the information contained herein. Refer to Standard Terms and Conditions of Sale and Performance Warranty documentation for additional information.