



PURON[®] HOLLOW FIBER MODULES

Hollow Fiber Submerged Membrane Modules for MBR Applications

PRODUCT DESCRIPTION

Membrane Chemistry:	Proprietary PVDF
Membrane Type:	Braided hollow fiber for outside-in operation
Fiber Support Chemistry:	Polyester
Nominal Pore Size:	0.03 μm
Outside Fiber Diameter:	0.1 inch (2.6 mm)
Regulatory Information:	Accepted by California Department of Public Health (CDPH) for compliance with California Water Recycling Criteria (Title 22)
Potting Material:	Proprietary epoxy compound
Module Frame Material:	316 Stainless Steel
Permeate Collection Tube Material:	ABS, PVC, PE manifolds
Storage Solution:	Glycerin

PRODUCT SPECIFICATIONS

Model	Membrane Area ft ² (m ²)	Rows per Module
PSH 95	1,020 (95)	3
PSH 440	4,735 (440)	14
PSH 520	5,597 (520)	14
PSH 1650	17,760 (1,650)	44

OPERATING & DESIGN INFORMATION*

Temperature Range:	41 - 104°F (5 - 40°C)
Maximum Filtration Transmembrane Pressure:	9 psi (0.6 bar)
Maximum Backflush Transmembrane Pressure:	9 psi (0.6 bar)
Allowable pH Range for Cleaning:	2.0 - 10.5
Maximum Allowed Total Chlorine @ 95°F (35°C) or Lower:	1,000 ppm @ pH 8 or higher during maintenance clean
Maximum Allowed Total Chlorine @ 95°F (35°C) or Lower:	2,000 ppm @ pH 8 or higher during recovery clean
Maximum Allowed Total Chlorine Contact:	500,000 ppm-hrs cumulative

* Consult Process Technology Group for specific applications.

NOMINAL DIMENSIONS & WEIGHT*

Model	L Inches (mm)	W Inches (mm)	H Inches (mm)	Dry Weight Pounds (kg)
PSH 95	17.55 (446)	35.16 (893)	81.10 (2,060)	361 (164)
PSH 440	28.74 (730)	69.10 (1,755)	84.16 (2,137)	1,017 (461)
PSH 520	28.74 (730)	69.10 (1,755)	97.13 (2,467)	1,157 (525)
PSH 1650	88.35 (2,244)	69.10 (1,755)	95.81 (2,434)	3,261 (1,479)

* See Outline drawings for details

CONNECTIONS

Model	Permeate		Air	
	Type	Size	Type	Size
PSH 95	Flange	DN 50	Flange	DN 50
PSH 440	Grooved Coupling	3" IPS	Grooved Coupling	2" IPS (2x)
PSH 520	Grooved Coupling	3" IPS	Grooved Coupling	2" IPS (2x)
PSH 1650	Grooved Coupling	6" IPS	Grooved Coupling	3" IPS (2x)

The information contained in this publication is believed to be accurate and reliable, but is not to be construed as implying any warranty or guarantee of performance. We assume no responsibility, obligation or liability for results obtained or damages incurred through the application of the information contained herein. Refer to Standard Terms and Conditions of Sale and Performance Warranty documentation for additional information