DIAION[™] WK40L

DIAION™ WK40L is an acrylic-type weakly acidic cation exchange resin. It has a higher total capacity than metacrylic type resins. A wide range of applications, especially in a field of dealkylization, demineralization and waste water treatment, is recommended.

Product		
Grade Name		DIAION TM WK40L
Туре		Weak Acid Cation
Matrix		Acrylic, Porous
Functional Group		Carboxylic Acid
Ionic Form		H ⁺
Specification		
Whole Bead Count	-	95 min.
Total Capacity	meq/mL	4.4 min.
Water Content	%	41 - 48
Particle Size Distribution on 1180 μm	%	10 max.
Particle Size Distribution thr. 425 μm	%	3 max.
Effective Size	mm	0.45 min.
Uniformity Coefficient	-	1.6 max.
Typical Properties		
Shipping Density	g/L	770
Mean Particle Size	μm	640
Particle Density	g/mL	1.19
Total Swelling (H ⁺ to Na ⁺)	%	73
Recommended Operating Conditions		
Maximum Operating Temperature	°C	120
Operating pH Range		4 - 14
Minimum Bed Depth	mm	800
Service Flow Rate	m/h	5 - 40
Regenerant		HCI
Regenerant Concentration	%	HCl 1 - 5
Regenerant Level	% of ionic load	110
Regenerant Flow Rate	m/h	2 - 6
Total Rince Requirement	BV	10 - 20





DIAION[™] WK40L

Hydraulic Characteristics

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of $\mathsf{DIAION}^\mathsf{TM}$ WK40L resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of WK40L




Fig. 2 Bed Expansion of WK40L

Notice

This information are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. The application, use and processing of our products are beyond our control and therefore your own responsibility.



