



FLUOROFLOW-SELECT Filter Cartridges

- liquid filters
- polytetrafluoroethylene (PTFE)


With FLUOROFLOW-SELECT filter cartridges, exceptional flow rates and on-stream life can be obtained in high temperature processes. The Select membrane pleat design results in higher flow rates and greater filter life and less down-time than a standard pleated configuration. The cartridge's all-fluoropolymer construction offers excellent chemical resistance.



Features and Benefits

- All fluoropolymer construction
- All filters are 100% integrity tested
- High flow rate increases throughput
- Select pleating provides high flow rates
- Compatible with most standard filter housings
- High temperature available

Performance Characteristics



Typically more than 44 scfm / psid for 0.05µm, more than 61 scfm / psid for 0.1µm and more than 82 for 0.2µm

10" Size (250 mm) Cartridge

FLUOROFLOW-SELECT Filter Cartridges

Specifications

Materials of Construction

- Filtration Membrane: Polytetrafluoroethylene (PTFE)
- Upstream Support: Polytetrafluoroethylene (PTFE)
- Downstream Support: Polytetrafluoroethylene (PTFE)
- Inner Support Core: PFA
- Outer Protection Cage: PFA
- End Caps: PFA
- Standard o-rings: FEP Encapsulated Silicone

Select Pleating



Recommended Operating Conditions

Temperature °C	Temperature °F	Max. Forward dP [bar]	Max. Forward dP [psid]
24	75	5.5	80.0
75	167	3.8	55.0
125	257	2.0	30.0
150	302	1.0	15.0

Temperature °C	Temperature °F	Max. Reverse dP [bar]	Max. Reverse dP [psid]
24	75	3.4	50.0
121	250	1.0	15.0

Integrity Test Values

Micron Rating	0.05	0.1	0.2	0.45	1.0
Diffusional Flow [bar]	2.8	1.5	0.9	0.5	0.2
Test Pressure [psig]	≥40	≥21	≥13	≥7	≥3

Tested in 60/40 IPA/DI water @ 25°C (77°F)

Particle Shedding

Wet-packed <2 particles / ml >0.2 µm after 26.5L @ 3.8L / min

Dry-packed <2 particles / ml >0.2 µm after 26.5L @ 3.8L / min

Metals Extractables

<20ppb (total) in a 10% HN03 extraction of 1.5 litres for 24 hours at ambient temperatures.

Applications

- Aggressive acids, bases and solvents
- Photolithography chemicals
- Ozonated and / or hot UPW

Ordering Information

FS - 18 - [] - [] - [] - E []

Code	End Fitting	Code	Length (Nominal)	Code	Micron	Code	Gasket / O-rings	Code	Options Treatment
2	226 / Flat	04	4" (125 mm)	423	0.03 µm	2	Silicone	Blank	UPW Flush
3	222 / Flat	10	10" (250 mm)	925	0.05 µm	4	Viton*	F	Ozone UPW Flush
7	226 / Fin	20	20" (500 mm)	001	0.1 µm	5	FEP-Endcapsulated Viton	W	Wet Packed
8	222 / Fin	30	30" (750 mm)	002	0.2 µm	6	FEP-Encapsulated Silicone		
		40	40" (1000 mm)	004	0.45 µm	7	Chemraz		
				010	1.0 µm	D	Kalrez		
						N	None		

LENNTECH bv

info@lenntech.com
www.lenntech.com
Tel. +31-15-261.09.00
Fax. +31-15-261.62.89

Parker domnick hunter has a continuous policy of product development and although the Company reserves the right to change specifications, it attempts to keep customers informed of any alterations. This publication is for general information only and customers are requested to contact our Process Filtration Sales Department for detailed information and advice on a products suitability for specific applications. All products are sold subject to the company's Standard conditions of sale.

*Viton is a registered trademark of E.I. DuPont de Nemours & Co., Inc.