

PRODUCT DATA SHEET

Purofine® PFA133S

Polystyrenic Macroporous, Weak
Base Anion Resin, Free Base form,
Uniform Particle Size, Sugar Grade

PRINCIPAL APPLICATIONS

- Demineralization - Sugar solutions
- Decolorization - Sugar Solutions

ADVANTAGES

- Uniform particle size

TYPICAL PACKAGING

- 1 ft³ Sack
- 25 L Sack
- 5 ft³ Drum (Fiber)
- 1 m³ Supersack
- 42 ft³ Supersack

LENNTECH
WATER TREATMENT Solutions

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Macroporous polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Tertiary Amine
Ionic Form	FB form
Total Capacity	1.8 eq/L (39.3 Kgr/ft ³) (FB form)
SBC	10 - 20 %
Moisture Retention	46 - 51 % (Cl ⁻ form)
Mean Diameter	550 ± 50 µm
Uniformity Coefficient	1.1 - 1.2
Reversible Swelling, FB → Cl ⁻ (max.)	25 %
Specific Gravity	1.04
Shipping Weight (approx.)	635 - 655 g/L (39.7 - 40.9 lb/ft ³)
Temperature Limit	100 °C (212.0 °F) (Cl ⁻ form)
Temperature Limit	60 °C (140.0 °F) (FB form)



LENNTECH

info@lennotech.com Tel. +31-152-610-900
www.lennotech.com Fax. +31-152-616-289