

Macroporous Weak Base Anion Exchange Resin

#### Basic Features:

Application	Demineralization
Polymer Structure	Macroporous polystyrene crosslinked with divinylbenzene
Appearance	Spherical beads
Functional Group	Primary Amine
Ionic form as shipped	Free Base

#### Typical Physical and Chemical Characteristics:

Total Capacity (min.)	Free Base	1.10 eq/l
Total Capacity (min.)	Free Base	24.02 kGr/ft <sup>3</sup>
Moisture Retention	Free Base	55-62 %
SBC		0-5 %
Mean Size Typical		0.60-0.85 mm
Uniformity Coefficient (max.)		1.70
Reversible Swelling (max.)	FB → Cl <sup>-</sup>	25 %
Specific Gravity		1.06 g/ml
Shipping Weight (approx.)		670-690 g/l
Shipping Weight (approx.)		41.9-43.1 lbs/ft <sup>3</sup>
Temp Limit	OH <sup>-</sup>	60 °C
Temp Limit	OH <sup>-</sup>	140 °F
Temp Limit	Cl <sup>-</sup>	100 °C
Temp Limit	Cl <sup>-</sup>	212 °F
pH Limits		0-14 (Stability)
pH Limits	H <sup>+</sup>	0-8 (Operating)



[info@lenntech.com](mailto:info@lenntech.com)  
[www.lenntech.com](http://www.lenntech.com)  
 Tel. +31-15-261.09.00  
 Fax. +31-15-261.62.89