

PRODUCT DATA SHEET

Purolite® A400TL

Polystyrenic Gel, Type I Strong
Base Anion Resin, Chloride form,
Trilite Mixed Bed System

PRINCIPAL APPLICATIONS

- Demineralization - Industrial
- Silica Removal

ADVANTAGES

- High operating capacity
- Efficient regeneration
- Exceptional physical stability
- Good kinetic performance

LENNTECH
WATER TREATMENT SOLUTIONS

SYSTEMS

- Trilite Systems
- Resin transfer

TYPICAL PACKAGING

- 1 ft³ Sack
- 25 L Sack
- 5 ft³ Drum (Fiber)
- 1 m³ Supersack
- 42 ft³ Supersack

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Gel polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Type I Quaternary Ammonium
Ionic Form	Cl ⁻
Total Capacity	1.3 eq/L (28.4 Kgr/ft ³) (Cl ⁻ form)
Moisture Retention	48 - 54 % (Cl ⁻ form)
Particle Size Range	425 - 850 µm
< 425 µm (max.)	1 %
Uniformity Coefficient (max.)	1.35
Reversible Swelling, Cl ⁻ → OH ⁻ (max.)	20 %
Shipping Weight (approx.)	670 - 690 g/L (41.9 - 43.1 lb/ft ³)
Temperature Limit	100 °C (212.0 °F) (Cl ⁻ form)
Temperature Limit	60 °C (140.0 °F) (OH ⁻ form)



LENNTECH

info@lennotech.com Tel. +31-152-610-900
www.lennotech.com Fax. +31-152-616-289