

## PRODUCT DATA SHEET

# Purolite® A600DL

Polystyrenic Gel, Type I Strong  
Base Anion Resin, Chloride form,  
Layered Bed grade

## PRINCIPAL APPLICATIONS

- Demineralization - Industrial

## ADVANTAGES

- High operating capacity
- Efficient regeneration



## SYSTEMS

- Layered Beds

## TYPICAL PACKAGING

- 1 ft<sup>3</sup> Sack
- 25 L Sack
- 5 ft<sup>3</sup> Drum (Fiber)
- 1 m<sup>3</sup> Supersack
- 42 ft<sup>3</sup> Supersack

## TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Gel polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Type I Quaternary Ammonium
Ionic Form	Cl <sup>-</sup> form
Total Capacity	1.4 eq/L (30.6 Kgr/ft <sup>3</sup> ) (Cl <sup>-</sup> form)
Moisture Retention	43 - 48 %
Particle Size Range	630 - 1200 µm
< 630 µm (max.)	5 %
Uniformity Coefficient (max.)	1.4
Reversible Swelling, Cl <sup>-</sup> → OH <sup>-</sup> (max.)	20 %
Specific Gravity	1.09
Shipping Weight (approx.)	685 - 720 g/L (42.8 - 45.0 lb/ft <sup>3</sup> )
Temperature Limit	100 °C (212.0 °F) (Cl <sup>-</sup> form)
Temperature Limit	60 °C (140.0 °F) (OH <sup>-</sup> form)



**LENNTECH**

info@lennotech.com Tel. +31-152-610-900  
www.lennotech.com Fax. +31-152-616-289