

PRODUCT DATA SHEET

Purolite® CT122/9048

Polystyrenic Gel, Strong Acid Cation
Resin, Hydrogen form, Catalyst

PRINCIPAL APPLICATIONS

- Bisphenol-A synthesis

TYPICAL PACKAGING

- 1 m³ Supersack
- 42 ft³ Supersack

LENNTECH
WATER TREATMENT SOLUTIONS

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Gel polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Sulfonic Acid
Ionic Form	H ⁺ form
Dry Weight Capacity (min.)	5 eq/kg (H ⁺ form)
Moisture Retention	78 - 82 % (H ⁺ form)
< 425 µm (max.)	2 %
< 850 µm (max.)	5 %
> 1400 µm (max.)	10 %
Shipping Weight (approx.)	700 - 730 g/L (43.8 - 45.6 lb/ft ³)
Temperature Limit	130 °C (266.0 °F)



LENNTECH
info@lennotech.com Tel. +31-152-610-900
www.lennotech.com Fax. +31-152-616-289