

PRODUCT DATA SHEET

Purolite® CT169

Polystyrenic Macroporous, Strong
Acid Cation Resin, Hydrogen form,
Catalyst

PRINCIPAL APPLICATIONS

- Phenol Alkylation
- MTBE Production
- TAME Production

TYPICAL PACKAGING

- 1 m³ Supersack
- 42 ft³ Supersack

LENNTECH
WATER TREATMENT Solutions

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Macroporous polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Sulfonic Acid
Ionic Form	H ⁺ form
Dry Weight Capacity (min.)	4.7 eq/kg
Moisture Retention	51 - 57 % (H ⁺ form)
Particle Size Range	425 - 1200 µm
< 425 µm (max.)	2 %
Uniformity Coefficient (max.)	1.7
Surface Area	35 - 50 m ² /g
Pore Volume	0.3 - 0.5 mL/g
Median Pore Diameter	250 - 425 Å
Specific Gravity	1.2
Shipping Weight (approx.)	755 - 790 g/L (47.2 - 49.4 lb/ft ³)
Temperature Limit	130 °C (266.0 °F)



LENNTECH


info@lennotech.com Tel. +31-152-610-900
www.lennotech.com Fax. +31-152-616-289

Hydraulic Characteristics

PRESSURE DROP

The pressure drop across a bed of ion exchange resin depends on the particle size distribution, bed depth, and voids volume of the exchange material, as well as on the flow rate and viscosity of the influent solution. Factors affecting any of these parameters—such as the presence of particulate matter filtered out by the bed, abnormal compressibility of the resin, or the incomplete classification of the bed—will have an adverse effect, and result in an increased head loss. Depending on the quality of the influent water, the application and the design of the plant, service flow rates may vary from 10 to 40 BV/h.

PRESSURE DROP ACROSS RESIN BED



BACKWASH

During up-flow backwash, the resin bed should be expanded in volume between 50 and 70% for at least 10 to 15 minutes. This operation will free particulate matter, clear the bed of bubbles and voids, and reclassify the resin particles ensuring minimum resistance to flow. When first putting into service, approximately 30 minutes of expansion is usually sufficient to properly classify the bed. It is important to note that bed expansion increases with flow rate and decreases with influent fluid temperature. Caution must be taken to avoid loss of resin through the top of the vessel by over expansion of the bed.

BACKWASH EXPANSION OF RESIN BED

