

PRODUCT DATA SHEET

Puromet™ MTS9501

Polystyrenic Macroporous,
Aminophosphonic Chelating Resin

PRINCIPAL APPLICATIONS

- Nickel Sulfate Purification

ADVANTAGES

- Highly selective

SYSTEMS

- Acidic liquors and pulps

TYPICAL PACKAGING

- 1 ft³ Sack
- 25 L Sack
- 5 ft³ Drum (Fiber)
- 1 m³ Supersack
- 42 ft³ Supersack



TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Macroporous polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Aminophosphonic
Ionic Form	Na ⁺ form
Calcium Capacity (min.)	26 g/L
Moisture Retention	60 - 68 % (Na ⁺ form)
< 300 µm (max.)	1 %
Uniformity Coefficient (max.)	1.5
Reversible Swelling, H ⁺ → Na ⁺ (max.)	50 %
Specific Gravity	1.13
Shipping Weight (approx.)	710 - 760 g/L (44.4 - 47.5 lb/ft ³)
Temperature Limit	80 °C (176.0 °F)



LENNTECH

info@lennotech.com Tel. +31-152-610-900
www.lennotech.com Fax. +31-152-616-289