

## PRODUCT DATA SHEET

# Purolite® NRW1160

Polystyrenic Gel, Strong Acid Cation  
Resin, Hydrogen form, Uniform  
Particle Size, Nuclear Grade

## PRINCIPAL APPLICATIONS

- Secondary circuit polishing
- Layering on Polishing Mixed Beds

## ADVANTAGES

- High operating capacity

## TYPICAL PACKAGING

- 1 CF Box
- 5 ft<sup>3</sup> Drum (Fiber)

**LENNTECH**  
WATER TREATMENT SOLUTIONS

## TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Gel polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Sulfonic Acid
Ionic Form	H <sup>+</sup> form
Total Capacity	2.5 eq/L (54.6 Kgr/ft <sup>3</sup> ) (H <sup>+</sup> form)
Moisture Retention	36 - 41 % (H <sup>+</sup> form)
Mean Diameter	625 ± 75 µm
Uniformity Coefficient (max.)	1.2
Conversion (min.)	99.9 % (H <sup>+</sup> form)
Impurities Iron (max.)	50 ppm
Impurities Sodium (max.)	40 ppm
Impurities Heavy Metals (max.)	40 ppm
Specific Gravity	1.23
Shipping Weight (approx.)	780 - 820 g/L (48.8 - 51.2 lb/ft <sup>3</sup> )
Temperature Limit	120 °C (248.0 °F)



**LENNTECH**

info@lenntech.com Tel. +31-152-610-900

www.lenntech.com Fax. +31-152-616-289