

Product Data Sheet

PUROLITE® NRW37Li

Nuclear Grade Mixed Bed

info@lenntech.com www.lenntech.com Tel. +31-15-261.09.00 Fax. +31-15-261.62.89

Nuclear Grade Mixed Bed Exchange Resin

Purolite NRW37 Li is a nuclear grade mixed bed resin especially designed for the removal of radioactive contaminants from primary circuits of nuclear power plants conditioned with natural lithium hydroxide. The product is an equilibrium mixture (chemical equivalents) of Purolite NRW100 carefully converted to the high purity natural lithium form, and Purolite NRW400 which is supplied highly converted to the hydroxide form. The mixture is capable of removing both cationic and anionic contaminants while maintaining the concentration of lithium hydroxide conditioner at near the correct dose level within the sealed circuit. All Purolite nuclear resins are supplied to exacting standards of high purity as given in the specifications below.

Basic Features:

Application Decontamination of Pressurized Water Reactor (PWR) Circuits

Polymer Structure Gel polystyrene crosslinked with divinylbenzene

Appearance Spherical beads

Functional Group Sulphonic Acid and Type 1 Quaternary Ammonium

lonic form as shipped Li⁺/OH⁻

Typical Physical and Chemical Characteristics:

Cation Component		Gel strong acid cation
Anion Component		Gel strong base anion
Cation / Anion Ratio		40/60 %
Total Capacity (min.)	H ⁺	1.80 eq/l
Total Capacity (min.)	H ⁺	39.30 kGr/ft ³
Total Capacity (min.)	OH-	1.00 eq/l
Total Capacity (min.)	OH ⁻	21.80 kGr/ft ³
Moisture Content		65 %
Mean Size Typical		0.65-0.90 mm
Uniformity Coefficient (max.)		1.70
Shipping Weight (approx.)		720-750 g/l
Shipping Weight (approx.)		45-46.9 lbs/ft ³
Temp Limit	Non ⁻ Regenerable Bed	100 °C



Product Data Sheet

PUROLITE® NRW37Li

Nuclear Grade Mixed Bed

Temp Limit	Non ⁻ Regenerable Bed	212 °F
Temp Limit	Regenerable Bed	60 °C
Temp Limit	Regenerable Bed	140 °F
pH Limits		0-14
CationicForm (min.)		99.90 %
Anionic Form(min.)	OH ⁻	95 %
Anionic Form(max.)	CO3-	5 %
Anionic Form(max.)	CI ⁻	0.10 %
Anionic Form(max.)	SO4 ⁻	0.30 %
Impurities Sodium (max.)		30 ppm
Impurities Iron (max.)		80 ppm
Impurities Heavy Metals		40 ppm

Lenntech

info@lenntech.com www.lenntech.com Tel. +31-15-261.09.00 Fax. +31-15-261.62.89