

PRODUCT DATA SHEET

Purolite® NRW700

Polystyrenic Gel, Type I Strong
Base Anion Resin, Hydroxide form,
Nuclear Grade

LENNTECH
WATER TREATMENT Solutions

PRINCIPAL APPLICATIONS

- Steam Generator blowdown purification
- CVCS Deborating of Primary coolant
- Radwaste decontamination
- Mixed Bed anion component

ADVANTAGES

- High operating capacity
- Minimal residual chlorides and sulfates
- Minimal residual metals
- Low organic extractables and rinseables
- Highly converted to hydroxide form

SYSTEMS

- Make up water demineralizers
- Primary Coolant
- Radwaste

TYPICAL PACKAGING

- 1 CF Box
- 5 ft³ Drum (Fiber)

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Gel polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Type I Quaternary Ammonium
Ionic Form	OH ⁻ form
Total Capacity	1.15 eq/L (25.1 Kgr/ft ³) (OH ⁻ form)
Moisture Retention	42 - 47 % (Cl ⁻ form)
Particle Size Range	425 - 1200 µm
< 425 µm (max.)	2 %
Uniformity Coefficient (max.)	1.7
Conversion (min.)	95 % (OH ⁻ form)
Impurities Iron (max.)	50 ppm
Impurities Sodium (max.)	20 ppm
Impurities Heavy Metals (max.)	30 ppm
Anionic Form, CO ₃ ²⁻ (max.)	5 %
Anionic Form, SO ₄ ²⁻ (max.)	0.1 %
Anionic Form, Cl ⁻ (max.)	0.1 %
Specific Gravity	1.08
Shipping Weight (approx.)	680 - 715 g/L (42.5 - 44.7 lb/ft ³)

Temperature Limit, Non-Regenerable Bed 100 °C (212.0 °F) (OH⁻ form)

Temperature Limit, Regenerable Bed 60 °C (140.0 °F) (OH⁻ form)



LENNTECH

info@lennotech.com Tel. +31-152-610-900
www.lennotech.com Fax. +31-152-616-289