

Macroporous Weak Base Anion Exchange Resin

Basic Features:

Application	Demineralization / Decolorization of Glucose Solutions
Polymer Structure	Macroporous Polystyrene Crosslinked with Divinylbenzene
Appearance	Spherical Beads
Functional Group	Tertiary Amine
Ionic form as shipped	Free Base

Typical Physical and Chemical Characteristics:

Total Capacity (min.)	Free Base	1.80 eq/l
Total Capacity (min.)	Free Base	39.30 kGr/ft ³
Moisture Retention	Cl ⁻	46 - 51 %
SBC		10 - 20 %
Mean Size Typical		0.5 - 0.6 mm
Uniformity Coefficient (max.)		1.2
Reversible Swelling (max.)	FB → Cl ⁻	25 %
Specific Gravity		1.04 g/ml
Shipping Weight (approx.)		635 - 655 g/l
Shipping Weight (approx.)		39.7 - 41.0 lbs/ft ³
Temp Limit	OH ⁻	60 °C
Temp Limit	OH ⁻	140 °F
Temp Limit	Cl ⁻	100 °C
Temp Limit	Cl ⁻	212 °F
pH Limits		0 - 14 (Stability)



info@lenntech.com
www.lenntech.com
 Tel. +31-15-261.09.00
 Fax. +31-15-261.62.89