

## PRODUCT DATA SHEET

# Purolite® XFA5000

Polystyrenic Macroporous, Type I  
Strong Base Anion Resin, Chloride  
form, Fine Mesh Grade

## PRINCIPAL APPLICATIONS

- Demineralization - SBA Component
- Acid Retardation
- Special applications

## ADVANTAGES

- Better kinetic performance
- Efficient rinse profile

**LENNTECH**  
WATER TREATMENT Solutions

## SYSTEMS

- Compressed Bed Depth System

## TYPICAL PACKAGING

- 1 ft<sup>3</sup> Sack
- 25 L Sack
- 5 ft<sup>3</sup> Drum (Fiber)
- 1 m<sup>3</sup> Supersack
- 42 ft<sup>3</sup> Supersack

## TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Macroporous polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Type I Quaternary Ammonium
Ionic Form	Cl <sup>-</sup> form
Total Capacity	1.15 eq/L (25.1 Kgr/ft <sup>3</sup> ) (Cl <sup>-</sup> form)
Moisture Retention	57 - 63 % (Cl <sup>-</sup> form)
Particle Size Range	150 - 425 µm
< 150 µm (max.)	1 %
Reversible Swelling, Cl <sup>-</sup> → OH <sup>-</sup> (max.)	20 %
Specific Gravity	1.08
Shipping Weight (approx.)	665 - 690 g/L (41.6 - 43.1 lb/ft <sup>3</sup> )
Temperature Limit	100 °C (212.0 °F) (Cl <sup>-</sup> form)
Temperature Limit	65 °C (149.0 °F) (OH <sup>-</sup> form)



**LENNTECH**

info@lennotech.com Tel. +31-152-610-900  
www.lennotech.com Fax. +31-152-616-289