



PRODUCT SPECIFICATION

8" ACM-LP Low Pressure RO Element Series

LENNTech

info@lenntech.com
www.lenntech.com
Tel. +31-152-610-900
Fax +31-152-616-289

Model	Permeate flow GPD (m ³ /day)*	Average Salt Rejection (%)	Minimum Salt Rejection (%)
8040-ACM5-TSAN	11,900 (45.0)	98.50	97.50

Performance is based on the following test conditions: 2,000.0 ppm NaCl, 150.0 psi, 25°C, 15% recovery, pH 8.0, 30 minutes operation.

OPERATIONAL AND DESIGN DATA

Membrane Type.....	ACM-LP Fully Aromatic Polyamide Low Pressure Advanced Composite
Configuration.....	Spiral Wound, Fiberglass Outer Wrap
Active Membrane Area.....	365 ft ² (33.5 m ²)
Recommended Applied Pressure.....	50 - 300 psi (3 - 21 bar)
Maximum Applied Pressure.....	600 psi (41 bar)
Recommended Operating Temperature.....	35 - 113°F (2 - 45°C)
Feedwater pH Range.....	2 - 11 continuous
Chlorine Tolerance.....	<0.1 ppm
Maximum Feed Flow.....	80 GPM (18 m ³ /hr)
Minimum Brine Flow/Permeate Flow Ratio....	5:1
Maximum SDI (15 minutes)	5.0
Maximum Turbidity.....	1 NTU



Element Weight : 45 (20)

Length (A) : 40.0 (1,016) Diameter (B) : 7.9 (200) Permeate Tube (C) : 1.50 (38.1)

Units in pounds and inches, units in parenthesis in kilograms and millimetres.

Mechanical Configuration: TriSep Style Core Tube

Feed Spacer: 0.031" thick diamond spacer

* Permeate flow is clean water flux at standard conditions above. Not applicable for all feedwater conditions. Individual element's permeate flow may vary +/- 15%.



**Engineered Membrane
SOLUTIONS**

LENNTech

info@lenntech.com Tel. +31-152-610-900
www.lenntech.com Fax. +31-152-616-289