



The Specialty Membrane Company

PRODUCT SPECIFICATION

8340 Cellulose Acetate TurboClean® Element

Model	Permeate Flow GPD (m ³ /day)*	Average Salt Rejection (%)	Minimum Salt Rejection (%)
TurboClean® Bev 8340-RO-CA-O	8,000 (30)	98.0	97.0

* Performance is based on the following test conditions: 2,000 ppm NaCl, 420 psi, 77°F (25°C), 15% recovery, pH 5.5, 30 minutes operation. Individual element permeate flow may vary +/- 15%.

OPERATIONAL AND DESIGN DATA

Membrane Type	SB20 Cellulose Acetate – Triacetate Blend Membrane
Configuration	Spiral Wound, Sanitary Style Element
Active Membrane Area	400 ft ² (37 m ²)
Typical Applied Pressure.....	200 - 500 psi (14 - 34 bar)
Maximum Applied Pressure	600 psi (41 bar)
Maximum Operating Temperature.....	90°F (32°C)
Feed pH Range	5.5 nominal, 4-7
Chlorine Tolerance	0.5 ppm nominal, 1.0 ppm maximum
Maximum Feed Flow	80 GPM (18 m ³ /hr)
Maximum Pressure Drop	15 psi (1 bar) per element; 60 psi (4 bar) across housing
Maximum SDI (15 minutes).....	5.0
Maximum Turbidity	1 NTU
Replaces Model	8340-O1E6Y2



Element Weight: 44 lbs. (20 kg)

Length (A): 40.0" (1,016 mm) Diameter (B): 8.3" (210 mm) Permeate Tube (C): 1.139" (29.0 mm)

Permeate Tube: Osmonics Style tube

Feed Spacer: 0.031" thick diamond spacer



**Engineered Membrane
SOLUTIONS**

LENNTech

info@lenntech.com Tel. +31-152-610-900

www.lenntech.com Fax. +31-152-616-289