



# PRODUCT SPECIFICATION

## 8" Continuous High Temperature NF Element

Model	Permeate Flow GPD (m <sup>3</sup> /day)*	Average Salt Rejection (%)	Minimum Salt Rejection (%)
<b>TurboClean® High Temp XN45-8040</b>	6,000 (22.7)	95.0	92.0

\* Performance is based on the following test conditions: 2,000 ppm MgSO<sub>4</sub>, 110 psi, 77°F (25°C), 15% recovery, pH 8.0, 30 minutes operation. Individual element permeate flow may vary +/- 15%.

### OPERATIONAL AND DESIGN DATA

Membrane Type .....	XN45 Advanced Polypiperazine Amide Nanofiltration Membrane
Configuration .....	Continuous High Temperature, Sanitary Style Element
Active Membrane Area .....	235 ft <sup>2</sup> (21.8 m <sup>2</sup> )
Typical Applied Pressure .....	50 - 300 psi (3 - 21 bar)
Maximum Applied Pressure .....	400 psi (27.6 bar) @ 158°F (70°C)
Maximum Operating Temperature .....	176°F (80°C)
Feedwater pH Range .....	3 - 9 continuous
Chlorine Tolerance .....	<0.1 ppm
Maximum Feed Flow .....	80 GPM (18 m <sup>3</sup> /hr)
Maximum Pressure Drop @ 50°C .....	15 psi (1 bar) per element; 60 psi (4 bar) across housing
Maximum Pressure Drop @ 70°C .....	5 psi (0.3 bar) per element; 20 psi (1.4 bar) across housing



Element Weight: 45 lbs. (20 kg)  
 Length (A): 40.00" (1,016 mm)      Diameter (B): 7.9" (200 mm)      Permeate Tube (C): 1.125" (28.6 mm)  
 Permeate Tube: FilmTec Style polysulfone tube



**Engineered Membrane**  
**SOLUTIONS**

LENNTECH

info@lennotech.com    Tel. +31-152-610-900  
 www.lennotech.com    Fax. +31-152-616-289