



# 3M™ Membrana™ DuraPES® Hydrophilic Flat Membrane, Type 600

General	
Intended use	Microfiltration
Available make-up configuration	Rolls

Chemical Composition	
Polymer	Polyethersulfone

Membrane Performance Characteristics	
Bubble point (water, 25 °C)	m 2.25 bar (≈32.63 psi) ± 0.35 bar (≈5.07 psi)
Transmembrane flow (water, 25 °C)	≥ 160 ml/(min cm <sup>2</sup> bar) ≥ 10249.24 ml/(min sq ft psi) ≥ 71.18 ml/(min sq in psi)
Retention of bacteria ( <i>Sacc. cerevisiae</i> )	≥7 log reduction value

Typical Physical Properties	
Thickness	m 140 μm (≈5.512 mil) ± 10 μm (≈0.394 mil)
Tensile strength	longitudinal ≥550 cN / 15 mm transversal ≥450 cN / 15 mm
Elongation at break	longitudinal ≥10% transversal ≥15%
Change of length	(steam, 121 °C) ≤ 3%

m = mean value

**Technical Information:** The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

**Product Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

**Warranty, Limited Remedy, and Disclaimer:** Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

3M and Membrana are trademarks of 3M Company. © 2016 3M Company. All rights reserved.



info@lennotech.com Tel. +31-152-610-900  
www.lennotech.com Fax. +31-152-616-289