# RE 1812-CE60

Innovative chlorine resistant RO element



LENNTECH info@lenntech.com Tel. +31-152-610-900

www.lenntech.com Fax. +31-152-616-289

for residential use

### **SPECIFICATIONS**

General **Features** 

| Model Name    | Permeate Flow Rate GPD (L/day) | Salt Rejection % |  |
|---------------|--------------------------------|------------------|--|
| RE1812 -CE 60 | 60 (227)                       | 98%              |  |

- 1. The stated product performance is based on data taken after 30 minutes of operationat the following test conditions:
  - 200 mg/L NaCl solution at 60 psig (0.41 MPa) applied pressure
  - 15% recovery
  - 77 °F (25 °C)
  - pH 6.5 -7.0
- 2. Permeate flow rate for each element may vary but will be no more than 1
- 3. Dry elements are packagedin a polyethylene bag  $^{\rm m}$  Wet elements are packaged in a polyethylene bag containing SB(4g/L) + HCl(0.51g/L) solution.


Thin-Film Composite Membrane type: Membrane material: Polyamide(PA)

Element configuration: Spiral-Wound, Tape W rapping

## Dimensions

| Model Name    | А      | В      | С       | D      | Е      |
|---------------|--------|--------|---------|--------|--------|
| RE1812 -CE6 0 | 0.67   | 0.87   | 11.73   | 0.98   | 1.77   |
|               | (17mm) | (22mm) | (298mm) | (25mm) | (45mm) |

<sup>\*</sup>All measurement are in inches



## RE1812 -CE60

Innovative chlorine resistant RO element

### for residential use



### APPLICATION DATA

**Operating Limits** 

Max. O peratingPressure
Max. Feed Flow Rate
Max. O peratingTemperature
Operating PH Range
Max. Turbidity
Max. SDI (1 5 min)

• Max. Chlorine Concentration < 0.1 mg/L

The information provided in this document is solely for informative purposes. It is the user's responsibility to ensure the propriate usage of this product. Woongjin Chemical assumes no obligation in ability or damages incurred for the misuse of the product or for the information provided in this document his document does not express or implies any warranty as to the merchantability or fitness of the products.

### GENERAL HANDLING PROCEDURES

Elements contained in the boxes must be kept dry at room temperature (7–32°C; 40 –95°F) and should not be stored in direct sunlight. If the polyethylene bag is damaged a new preservative solution (sodium bisulfite) must be added and airtight seabd to prevent drying and biological growth.

Permeate from the first hour of operation should be discarded to flush out the preservative solution.

Elements should be immersed in a preservative solution during storage, shipping and system shutdowns to prevent biological gowth and freezing. The standard storage solution contains 1% by weight sodium bisulfite or sodium metabisulfite (food grade). For short term storage (i.e. one week or less) 1% by weight sodium metabisulfite solution is adequate for preventing biologicalrgwth.

Keep elements moist at all times after initial wetting.

Only use chemicals compatible with the membrane elements and components. Use of such chemicals may void the element limited warranty.

Permeate pressure must always be equal  $\sigma$  less than the feed/concentrate pressure. Damage caused by permeate back pressure voids the element limited warranty.