

**DOWEX™ MONOSPHERE™ 650HXC NG (H)**

A High Cross-linked Uniform Particle Size Strong Acid Cation Exchange Resin
for Condensate Polishing Applications

Product	Type	Matrix	Functional group
DOWEX™ MONOSPHERE™ 650HXC NG (H)	Strong acid cation	Styrene-DVB, gel	Sulfonic acid

Guaranteed Sales Specifications			H ⁺ form			
Total exchange capacity, min.		eq/L	2.2			
Water retention capacity		%	39-44			
Bead size distribution						
Volume median diameter		µm	650±50			
Uniformity coefficient, max.			1.1			
> 850 µm, max.		%	5			
< 300 µm, max.		%	0.5			
Whole uncracked beads, min.		%	95			
Friability (Crush strength)						
Average, min.		g/bead	500			
> 200 g/bead, min.		%	95			
Ionic conversion, min.		%	99.7			
Trace metals, ppm dry resin, max.						
Na	Fe	Cu	Al	Ni	Zn	Heavy Metals (as Pb)
50	50	50	50	10	10	20

Typical Physical and Chemical Properties			H ⁺ form
Total swelling (Na ⁺ ⇒ H ⁺)		%	6
Particle density		g/mL	1.26
Shipping weight**		g/L lbs/ft ³	816 51

Recommended Operating Conditions	• Maximum operating temperature	130°C (265°F)
	• pH range	0-14
	• Bed depth in mixed bed, min.	450 mm (1.5 ft)
	• Flow rates: Service/condensate polishing Backwash Regenera- tion/displacement rinse	40-150 m/h (16-60 gpm/ft ²) See figure 2
	• Total rinse requirement	1-10 m/h (0.4-4 gpm/ft ²)
	• Regenerant	3-6 Bed volumes 1-10% H ₂ SO ₄ or 4-8%HCl

** As per the backwashed and settled density of the resin, determined by ASTM D-2187.

Typical properties and applications


DOWEX™ MONOSPHERE™ 650HXC NG (H) strong acid cation exchange resin is a nuclear grade high capacity gel resin with uniform particle size designed especially for use in non-regenerable deep bed condensate polishers together with DOWEX MONOSPHERE 550A (OH) at boiling water reactor (BWR) power stations. The resin attributes an outstanding stability against oxidative conditions to its higher cross-linkage (14%-DVB) and prevents surface kinetic impairment of anion resins due to smaller amounts of high molecular weight TOC leachables.

Packaging

5 cubic feet fiber drums.

Figure 1. Pressure Drop vs. Flow Rate

For DOWEX MONOSPHERE 650HXC NG (H), 20°C (68°F)



For other temperatures use:

$$P_T = P_{20^\circ\text{C}} / (0.026T_{\text{C}} + 0.48), \text{ where } P \equiv \text{bar/m}$$

Warning: Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.

Notice: No freedom from any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

