

**AMBERLITE™ FPA42 Cl Ion Exchange Resin**

Food-grade, Gel, Strong Base Anion Exchange Resin

**Description**

AMBERLITE™ FPA42 Cl Ion Exchange Resin is a high-capacity, uniform particle size, gel, Type I strong base anion exchanger. It is intended for general demineralization and deashing in which the risk of fouling from colored bodies and organics is relatively low.

The uniformity and mean particle size of AMBERLITE™ FPA42 Cl have been optimized for use in equipment including mixed beds. AMBERLITE™ FPA42 Cl can be directly substituted for conventional gel anion exchange resin in new equipment and in rebeds of existing demineralizers.

**Applications**

- Sweetener deashing
- Demineralization

**Typical Properties**

---

<b>Physical Properties</b>	
Copolymer	Styrene-divinylbenzene
Matrix	Gel
Type	Strong base anion, Type I
Functional Group	Trimethylammonium
Physical Form	Amber, translucent, spherical beads

---

<b>Chemical Properties</b>	
Ionic Form as Shipped	Cl <sup>-</sup>
Total Exchange Capacity	≥ 1.30 eq/L
Water Retention Capacity	49 – 55%

---

<b>Particle Size</b> §	
Particle Diameter	600 – 800 μm
Uniformity Coefficient	≤ 1.25
< 425 μm	≤ 0.5%
> 850 μm	≤ 5.0%

---

<b>Stability</b>	
Swelling	Cl <sup>-</sup> → OH <sup>-</sup> : 30%

---

<b>Density</b>	
Particle Density	1.06 – 1.08 g/mL
Shipping Weight	670 g/L

---

§ For additional particle size information, please refer to the [Particle Size Distribution Cross Reference Chart](#) (Form No. 177-01775).

## Suggested Operating Conditions

Bed Depth, min.	800 mm (2.6 ft)
Flowrates	
Service	5 – 50 BV*/h
Linear Velocity	≤ 60 m/h
Backwash	See Figure 1
Slow Rinse	Regeneration flowrate for 2 BV
Fast Rinse (if applicable)	Service flowrate for 3 – 6 BV
Contact Time	
Regeneration	≥ 20 minutes
Regenerant	
Concentration	NaOH
Level	2 – 5%
	40 – 100 kg/m <sup>3</sup> (2.5 – 6.3 lb/ft <sup>3</sup> )

\* 1 BV (Bed Volume) = 1 m<sup>3</sup> solution per m<sup>3</sup> resin or 7.5 gal per ft<sup>3</sup> resin


## Hydraulic Characteristics

Estimated bed expansion of AMBERLITE™ FPA42 Cl Ion Exchange Resin as a function of backwash flowrate and temperature is shown in Figure 1.

Estimated pressure drop (in water) for AMBERLITE™ FPA42 Cl as a function of service flowrate and temperature is shown in Figure 2. These pressure drop expectations are valid at the start of the service run with clean water and a well-classified bed.


**Figure 1: Backwash Expansion**

Temperature = 5 – 40°C (41 – 104°F)



**Figure 2: Pressure Drop**

Temperature = 5 – 60°C (41 – 140°F)



## Product Stewardship

DuPont has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with DuPont products—from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

## Customer Notice

DuPont strongly encourages its customers to review both their manufacturing processes and their applications of DuPont products from the standpoint of human health and environmental quality to ensure that DuPont products are not used in ways for which they are not intended or tested. DuPont personnel are available to answer your questions and to provide reasonable technical support. DuPont product literature, including safety data sheets, should be consulted prior to use of DuPont products. Current safety data sheets are available from DuPont.

Please be aware of the following:

- **WARNING:** Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.



All information set forth herein is for informational purposes only. This information is general information and may differ from that based on actual conditions. Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where DuPont is represented. The claims made may not have been approved for use in all countries. Please note that physical properties may vary depending on certain conditions and while operating conditions stated in this document are intended to lengthen product lifespan and/or improve product performance, it will ultimately depend on actual circumstances and is in no event a guarantee of achieving any specific results. DuPont assumes no obligation or liability for the information in this document. References to "DuPont" or the "Company" mean the DuPont legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. No freedom from infringement of any patent or trademark owned by DuPont or others is to be inferred.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, ℠ or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted. © 2019 DuPont.

