

AmberLite™ FPA90RF Cl Ion Exchange Resin

Food-grade, Reduced Fines, Styrenic, Macroporous, Strong Base Anion Exchange Resin for Cane Sugar Decolorization

Description

AmberLite™ FPA90RF Cl Ion Exchange Resin has been specially designed for the decolorization of liquid sugar syrups. Ion exchange based decolorization technology has been used more effectively and economically than carbon or bone char based technologies. Sugar refiners and soft drink bottlers around the world have installed AmberLite™ FPA90RF Cl to successfully decolorize sucrose solutions.

AmberLite™ FPA90RF Cl is a styrenic, macroporous, Type I strong base anion resin. It is an excellent choice for cane sugar decolorization, offering advantages such as:

- Maximum decolorization efficiency due to the macroporous structure
- Particle size distribution specifically selected to give optimal performance in packed bed and **up-flow** floating bed systems
- Exceptional physical stability, excellent resistance to osmotic shock, and very good organic fouling resistance

AmberLite™ FPA90RF Cl reduced fines resin is often used in conjunction with AmberLite™ 14i Inert Resin, which floats and prevents resin fines from entering the distribution system.

Styrenic AmberLite™ FPA90RF Cl can be used as a single component or following acrylic AmberLite™ FPA98 Cl Ion Exchange Resin for highly-colored feed solutions.

Applications

- Cane sugar decolorization

Typical Properties

Physical Properties	
Copolymer	Styrene-divinylbenzene
Matrix	Macroporous
Type	Strong base anion, T type I
Functional Group	Trimethylammonium
Physical Form	Off-white, opaque, spherical beads
Chemical Properties	
Ionic Form as Shipped	Cl ⁻
Total Exchange Capacity	≥ 1.00 eq/L
Water Retention Capacity	58 – 64%
Particle Size [§]	
Particle Diameter	650 – 820 μm
Uniformity Coefficient	≤ 1.5
< 300 μm	≤ 0.1%
> 1180 μm	≤ 2.0%
Stability	
Swelling	Cl ⁻ → OH ⁻ : ~25%
Density	
Particle Density	1.050 – 1.080 g/mL
Shipping Weight	700 g/L

[§] For additional particle size information, please refer to the [Particle Size Distribution Cross Reference Chart](#) (Form No. 45-D00954-en).

Suggested Operating Conditions

Maximum Operating Temperature (Cl ⁻ form)	80°C (176°F)
Bed Depth, min.	1000 mm (3.3 ft)
Flowrates	
Service	2 – 4 BV*/h (or up to 8 BV/h)
Sweeten-off	Service flowrate for 1.5 – 2 BV
Backwash	See Figure 1
Regeneration	2 BV/h
Slow Rinse	2 BV/h
Sweeten-on	Service flowrate for 1 BV
Contact Time	
Regeneration	≥ 45 – 60 minutes
Displacement Rinse	≥ 60 minutes
Total Rinse Requirement	5 BV
Regenerant	
Concentration	10% NaCl 0.2% NaOH
Level, 100% basis	
Co-current	180 – 200 kg/m ³ (11.3 – 12.5 lb/ft ³)
Counter-current	150 kg/m ³ (9.4 lb/ft ³)
Temperature	25 – 70°C (77 – 158°F)


* 1 BV (Bed Volume) = 1 m³ solution per m³ resin or 7.5 gal solution per ft³ resin

Hydraulic Characteristics

Bed expansion of AmberLite™ FPA90RF CI Ion Exchange Resin as a function of backwash flowrate and temperature is shown in Figure 1.

Figure 1: Backwash Expansion

Temperature = 5 – 60°C (41 – 140°F)



Product Stewardship

DuPont has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with DuPont products—from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

DuPont strongly encourages its customers to review both their manufacturing processes and their applications of DuPont products from the standpoint of human health and environmental quality to ensure that DuPont products are not used in ways for which they are not intended or tested. DuPont personnel are available to answer your questions and to provide reasonable technical support. DuPont product literature, including safety data sheets, should be consulted prior to use of DuPont products. Current safety data sheets are available from DuPont.

Please be aware of the following:

- **WARNING:** Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.

LENNTECH

WATER TREATMENT SOLUTIONS

info@lennotech.com Tel. +31-152-610-900

www.lennotech.com Fax. +31-152-616-289

All information set forth herein is for informational purposes only. This information is general information and may differ from that based on actual conditions. Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where DuPont is represented. The claims made may not have been approved for use in all countries. Please note that physical properties may vary depending on certain conditions and while operating conditions stated in this document are intended to lengthen product lifespan and/or improve product performance, it will ultimately depend on actual circumstances and is in no event a guarantee of achieving any specific results. DuPont assumes no obligation or liability for the information in this document. References to "DuPont" or the "Company" mean the DuPont legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. No freedom from infringement of any patent or trademark owned by DuPont or others is to be inferred.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, ℠ or ® are owned by affiliates of DuPont de Nemours Inc. unless otherwise noted. © 2020 DuPont.

