



Lewatit® A 365 is a premium food grade, macroporous, weak base anion exchange resin based on a polyacrylate polymer. **Lewatit® A 365** is designed to offer exceptional high operating capacity, good physical stability and excellent resistance to mechanical osmotic shock.

The acrylic matrix of **Lewatit® A 365** offers rapid kinetics for common anions, including larger, more bulky, anions like sulfate. **Lewatit® A 365** is fully regenerable with NaOH and other weak bases. As **Lewatit® A 365** is a true weak base resin, the regenerant consumption is close to stoichiometric.

Lewatit® A 365 is recommended for applications including demineralization of high TDS waters, selective sulfate removal, purification of aqueous solutions, including decolorization applications and once-through cartridge applications.

Lewatit® A 365 is supplied in a heterodispersed particle size distribution as spherical beads in the fully swollen most free base form. **Lewatit® A 365** is prepared with a minimum amount of fines resulting in low pressure losses during the service.

If using **Lewatit® A 365** to treat potable water and the aqueous solutions listed above, special care should be given to the initial cycles of the new resin. Please refer to the recommended start-up conditions available on request.

The special properties of this product can only be fully utilized if the technology and process used correspond to the current state-of-the-art. Further advice in this matter can be obtained from Lanxess, Business Unit Liquid Purification Technologies.

This document contains important information and must be read in its entirety.





Common Description

Delivery form	Free base
Functional group	Polyamine
Matrix	Acrylic
Structure	Macroporous
Appearance	Yellow, white, opaque

Specified Data

Uniformity coefficient		max.	1.8
Mean bead size	d50	mm	0.4-1.6
Effective size	d10	mm	min. 0.40
Total capacity (delivery		min. eq/L	3.4
form)			

This document contains important information and must be read in its entirety.





Typical Physical and Chemical Properties

Bulk density for shipment (+/- 5%)	g/L	720
Density	approx. g/mL	1.1
Water retention (delivery form)	approx. weight %	43-54
Volume change (free base - Cl ⁻)	max. approx. %	25
Stability pH range		0-14
Stability temperature range	°C	1-60
Storage time (after delivery)	max. years	2
Storage temperature range	°C	-20 - +40

Operation

Operating temperature		max. °C	60
Operating pH range	during exhaustion		0-8
Bed depth for single column		min. mm	800
Back wash bed expansion per m/h (20°C)		%	17
Specific pressure loss kPa*h/m² (15°C)		kPa*h/m² (15°C)	1
Max. pressure loss during operation		kPa	200
Specific flow rate		max. BV/h	5-30
Freeboard	during backwash	min. vol. %	80

Regeneration

NaOH regeneration	concentration	approx. wt. %	2-5
NaOH regeneration	quantity co-current	min. g/L resin	160
NaOH regeneration	quantity counter-current	min. g/L resin	100
Regeneration contact		min. minutes	30
time			
Slow rinse at		min. BV	2
regeneration flow rate			
Fast rinse at service flow		min. BV	4
rate			

This document contains important information and must be read in its entirety.





Additional Information & Regulations

Safety precautions

Strong oxidants, e.g. nitric acid, can cause violent reactions if they come into contact with ion exchange resins

Toxicity

The safety data sheet must be observed. It contains additional data on product description, transport, storage, handling, safety and ecology.

Disposal

In the European Community Ion exchange resins have to be disposed, according to the European waste nomenclature which can be accessed on the internet-site of the European Union.

Storage

It is recommended to store ion exchange resins at temperatures above the freezing point of water under roof in dry conditions without exposure to direct sunlight. If resin should become frozen, it should not be mechanically handled and left to thaw out gradually at ambient temperature. It must be completely thawed before handling or use. No attempt should be made to accelerate the thawing process.

Packaging

The experience has shown that the packaging stability for reliable resin containment is limited to 24 months under the storage conditions described above. It is therefore recommended to use the product within this time frame; otherwise the packaging condition should be checked regularly.



This information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

This document contains important information and must be read in its entirety.

