

For the production of ultrapure water (> 18 MOhm*cm at 25 °C).

Lewatit® UltraPure 1243 MD is a highly regenerated, specially cleaned, strongly basic, gelular anion exchanger with a uniform particle bead size distribution.

Lewatit® UltraPure 1243 MD meets international standards for applications in the semiconductor industry with extremely low TOC-leaching and a high operating capacity for "non-regenerable" applications.

Due to its high chemical and mechanical stability, **Lewatit® UltraPure 1243 MD** can be used either as a anion polisher (delta TOC < 10 ppb) or in a polishing mixed bed (delta TOC < 5 ppb) together with **Lewatit® UltraPure 1213 MD**.

Test certificates for ionic leachables can be provided on request.

The special properties of this product can only be fully utilized if the technology and process used correspond to the current state-of-the-art. Further advice in this matter can be obtained from Lanxess, Business Unit Ion Exchange Resins.

General Description

Ionic form as shipped	OH ⁻
Functional group	quaternary amine, type I
Matrix	crosslinked polystyrene
Structure	gel type beads
Appearance	light brown, translucent

Physical and Chemical Properties

		metric units	
Uniformity Coefficient*		max.	1.1
Mean bead size*		mm	0.6 (+/- 0.07)
Bulk density (+/- 5 %)		g/l	650
Density		approx. g/ml	1.08
Water retention		wt. %	55 - 65
Total capacity*		min. eq/l	1.1
Volume change	OH ⁻ --> Cl ⁻	max. vol. %	-22
Stability	at pH-range		0 - 14
Storability	of the product	max. months	3
Storability	temperature range	°C	4 - 24
TOC release* (a. 80 BV)	as single component	max. ppb	3
Resistivity effluent* (a. 80 BV)	as single component	min.MOhm*cm	17

* Specification values subjected to continuous monitoring.

Recommended Operating Conditions*

		metric units	
Operating temperature		max. °C	40
Operating pH-range			0 - 14
Specific pressure drop	(15 °C)	approx. kPa*h/m ²	1.0
Pressure drop		max. kPa	200
Linear velocity	operation	max. m/h	60
Rinse water requirement	slow / fast	approx. BV	80
Mixed bed operation			
Bed depth		min. mm	500
Anion polisher operation			
Bed depth		min. mm	800
Regenerant	type		NaOH**
Regeneration	level	approx. g/l	200
Regeneration	concentration	approx. wt. %	2 - 6
Regeneration	contact time	minutes	> 30
Linear velocity	regeneration	approx. m/h	min. 5

* The recommended operating conditions refer to the use of the product under normal operating conditions. It is based on tests in pilot plants and data obtained from industrial applications. However, additional data are needed to calculate the resin volumes required for ion exchange units. These data are to be found in our Technical Information Sheets.

** After regeneration the listed TOC and resistivity figures might not be achieved again.

Additional Information & Regulations

Safety precautions

Strong oxidants, e.g. nitric acid, can cause violent reactions if they come into contact with ion exchange resins.

Toxicity

The safety data sheet must be observed. It contains additional data on product description, transport, storage, handling, safety and ecology.

Disposal

In the European Community ion exchange resins have to be disposed, according to the European waste nomenclature which can be accessed on the internet-site of the European Union.

Storage

It is recommended to store ion exchange resins at temperatures above the freezing point of water under roof in dry conditions without exposure to direct sunlight. If resin should become frozen, it should not be mechanically handled and left to thaw out gradually at ambient temperature. It must be completely thawed before handling or use. No attempt should be made to accelerate the thawing process.

This information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

This document contains important information and must be read in its entirety.

Edition: 2011-10-13
Previous Edition: 2011-05-12

LENNTECH

WATER TREATMENT SOLUTIONS

info@lennotech.com Tel. +31-152-610-900

www.lennotech.com Fax. +31-152-616-289

For more information or a quote, please use the