## DIAION<sup>™</sup> UBA120OH

DIAION™ UBA120OH is an anion exchange resin with a uniform particle size. It has a standard cross-linkages and excellent properties. A wide range of applications, especially in a field of manufacturing and processing pure water, is recommended.

Product		
Grade Name		DIAION <sup>TM</sup> UBA120OH
Туре		Strong Base Anion
Matrix		Styrene-DVB, Gel
Functional Group	Ту	pe I (trimethyl ammonium groups)
lonic Form		OH <sup>-</sup>
Specification		
Whole Bead Count	-	90 min.
Salt Splitting Capacity	meq/mL	1.0 min.
Water Content	%	62 - 70
Average Diameter	μm	620 ± 50
Uniformity Coefficient	-	1.10 max.
Ionic Conversion (OH <sup>-</sup> )	%	90 min.
Typical Properties		
Shipping Density	g/mL	675
Particle Density	g/mL	1.07
Total Swelling (Cl to OH)	%	24
Recommended Operating Conditions		
Maximum Operating Temperature	°C	80 (Cl <sup>-</sup> )
		60 (OH <sup>-</sup> )
Operating pH Range		0 - 14
Minimum Bed Depth	mm	800
Service Flow Rate	m/h	10 - 60
Regenerant		NaOH
Regenerant Concentration	%	NaOH 2 - 8
Regenerant Level	g/L	50 - 200
Regenerant Flow Rate	m/h	2 - 8
Total Rince Requirement	BV	2 - 10





# **DIAION**<sup>TM</sup>

### **UBA1200H**

#### **Hydraulic Characteristics**

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of DIAION<sup>TM</sup> UBA120OH resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of UBA120OH




Fig. 2 Bed Expansion of UBA120OH

#### **Notice**

This information are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. The application, use and processing of our products are beyond our control and therefore your own responsibility.

No.01-04-A-0401



