# **DIAION™ UBK04H**

DIAION™ UBK04H is a cation exchange resin with a uniform particle size. It has 4% cross-linkages and excellent properties. A wide range of applications, especially in a field of catalysts, is recommended.

Product		
Grade Name		DIAION <sup>™</sup> UBK04H
Туре		Strong Acid Cation
Matrix		Styrene-DVB, Gel
Functional Group		Sulfonic acid
Ionic Form		H <sup>+</sup>
Specification		
Whole Bead Count	-	95 min.
Salt Splitting Capacity	meq/mL	1.2 min.
Water Content	%	65 - 70
Average Diameter	μm	$500 \pm 50$
Uniformity Coefficient	-	1.2 max.
Ionic Conversion (H <sup>+</sup> )	%	95 min.
Typical Properties		
Shipping Density	g/mL	840
Particle Density	g/mL	1.13
Total Swelling (Na <sup>+</sup> to H <sup>+</sup> )	%	9
Recommended Operating Condit	ions	
Maximum Operating Temperature	°C	120
Operating pH Range		0 - 14
Minimum Bed Depth	mm	800
Service Flow Rate	m/h	10 - 40
Regenerant		HCI
		$H_2SO_4$
Regenerant Concentration	%	HCl 4 - 10
		H <sub>2</sub> SO <sub>4</sub> 1 - 4
Regenerant Level	g/L	30 - 150
Regenerant Flow Rate	m/h	2 - 10
Total Rince Requirement	BV	2 - 10





### **DIAION**

## **UBK04H**

#### **Hydraulic Characteristics**

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of  $\mathsf{DIAION}^\mathsf{TM}$  UBK04H resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of UBK04H




Fig. 2 Bed Expansion of UBK04H

#### **Notice**

This information are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. The application, use and processing of our products are beyond our control and therefore your own responsibility.

No.01-02-A-0101



