OLTREMARE
LIQUID SEPARATION

Model LOW1-4641

Low Energy, Very High Rejection - Brackish Water Element

Туре	Configuration: Spiral Wound		Membrane Polymer: Composite Polyamide		Brine Spacer Material: Polypropylene	
Specifications	Permeate Flow:	* Permeate Flow:		Salt Rejection:	Nominal Membrane Area: 120ft ² (11,2m ²)	
	3600 gpd (13,6 m³/d)	5200 gpd (19,7 m³/d)		99,1% nominal (98,5% minimum)		
Test Conditions (After 30 min of operation)	Applied Pressure:	* Applied Pressure:	Solution NaCl	Operating Temperature:	Permeate Recovery:	pH Range:
	150 psi <i>(10,3 bar)</i>	225 psi (15,5 bar)	1500 ppm	77 °F (25 °C)	15%	6,5 ÷ 7,0

Dimensions

				_	
A	B	C	D _F	D _C	Weight
Total	ATD	Connection	Core Tube I	Extension	
Length	Diameter	Diameter	Feed Side	Conc. Side	
41.3 inches	4.6 inches	0.75 inches	0.0 inches	2.19 inches	11 lbs
<i>(1049 mm)</i>	(116,8 mm)	<i>(19,1 mm)</i>	<i>(0,0 mm)</i>	(55,6 mm)	(5,0 Kg)
(F)D (F)D T B	PLUG	A		 P Permeate F Feed Cn Concentration 	

Maximum Operating Limits							
Operatin Fiberglassed	g Pressure Tape Wrapped	Temperature	Pressure Drop	Feed Flow	Chlorine Concentratio	Feedwater n SDI (15min)	Feedwater Turbidity
600 psi (41,4 bar)	300 psi (20,7 bar)	113 °F <i>(4</i> 5 °C)	10 psi <i>(0,7 bar)</i>	18 gpm <i>(4,1 m³/h)</i>	<0,1 ppm	5,0	1,0 NTU
Other Operating Limits				Feedwate pH	er Minimum ratio of concen permeate flow for any el		
				3,0 ÷ 10,0)	5:1	

The limitations shown in Operating Limits are for general use. The values may be more conservative for specific projects to ensure the best performance and longest life of the membrane.

Notice: Minimum permeate flow for individual elements 15 percent below listed flow. Elements are vacuum sealed in a polyethylene bag containing less than 1.0% sodium meta-bisulfite and 10% propylene glycol solution.

Guidelines: Permeate obtained from first hour of operation should be discarded.

Avoid static permeate-side backpressure at all times.

These membranes may be subject to drinking water application restrictions in some countries: please check the application status before use and sale.

For element loading use only glycerine to lubricate o-rings and brine seal.

The customer is fully responsible for the effects of incompatible chemicals on elements. The presence of free chlorine and other oxidizing agents will cause membrane failure, the damage is not covered under warranty. Oltremare believes the information and data contained herein to be accurate and useful. The information and data are offered in good

Oltremare believes the information and data contained herein to be accurate and useful. The information and data are offered in good faith, but without guarantee, as conditions and methods of use of our products are beyond our control. Oltremare assumes no liability for results obtained or damages incurred through the application of the presented information and data. It is the user's responsibility to determine the appropriateness of Oltremare's products for the user's specific end uses.

No performance warranties are given; all implied warranties of merchantability or fitness for a particular purpose are expressly excluded. Consult factory for detailed warranty information.

We reserve the right to modify or amend specifications without prior notice.

