

Model LOW2-2540

Low Energy, Excellent Rejection - Brackish Water Element

Туре	Configuration: Spiral Wound		embrane Polymer: mposite Polyamide		cer Material: ropylene
Specifications	Permeate Flow: 550 gpd (2,1 m³/d)		Salt Rejection: 99,4% nominal (99,0% minimum)		al Membrane Area: 28ft² (2,6m²)
Test Conditions (After 30 min of operation)	Solution NaCl 1500 ppm	Applied Pressure: 150 psi (10,3 bar)	Operating Temperature: 77 °F (25 °C)	Permeate Recovery: 10%	pH Range: 6,5 ÷ 7,0

Dimensions

B ATD Diameter	C Connection Diameter	D _F Core Tube I Feed Side	D _C Extension Conc. Side	Weight
2.4 inches (61 mm)	0.75 inches (19,1 mm)	1.2 inches (30,5 mm)	1.2 inches (30,5 mm)	4 lbs (1,8 Kg)
D _F	Α		F Feed	
	ATD Diameter 2.4 inches (61 mm)	ATD Connection Diameter 2.4 inches (61 mm) (19,1 mm)	ATD Connection Diameter Diameter Feed Side 2.4 inches (61 mm) (19,1 mm) (30,5 mm) A Population Diameter Feed Side 1.2 inches (30,5 mm)	ATD Connection Core Tube Extension Diameter Diameter Feed Side Conc. Side 2.4 inches 0.75 inches 1.2 inches 1.2 inches (61 mm) (30,5 mm) (30,5 mm) A P Permeate

Maximum Operating Limits

Operat	ng Pressure	Temperature	Pressure	Feed	Chlorine	Feedwater	Feedwater
Fiberglassed	Tape Wrapped		Drop	Flow	Concentration	SDI (15min)	Turbidity
600 psi (41,4 bar)	300 psi <i>(20,7 bar)</i>	113 °F <i>(4</i> 5 °C)	10 psi <i>(0,7 bar)</i>	6 gpm (23 lpm)	<0,1 ppm	5,0	1,0 NTU

Other Operating Limits	Feedwater pH	Minimum ratio of concentrate to permeate flow for any element
	3.0 ÷ 10.0	5:1

The limitations shown in Operating Limits are for general use. The values may be more conservative for specific projects to ensure the best performance and longest life of the membrane.

Notice: Minimum permeate flow for individual elements 15 percent below listed flow. Elements are vacuum sealed in a polyethylene bag containing less than 1.0% sodium meta-bisulfite.

Guidelines: Permeate obtained from first hour of operation should be discarded.

Avoid static permeate-side backpressure at all time.

These membranes may be subject to drinking water application restrictions in some countries: please check the application status before use and sale.

For element loading use only glycerine to lubricate o-rings and brine seal.

The customer is fully responsible for the effects of incompatible chemicals on elements. The presence of free chlorine and other oxidizing agents will cause membrane failure, the damage is not covered under warranty.

Oltremare believes the information and data contained herein to be accurate and useful. The information and data are offered in good faith, but without guarantee, as conditions and methods of use of our products are beyond our control. Oltremare assumes no liability for results obtained or damages incurred through the application of the presented information and data. It is the user's responsibility to determine the appropriateness of Oltremare's products for the user's specific end uses.

No performance warranties are given; all implied warranties of merchantability or fitness for a particular purpose are expressly excluded. Consult factory for detailed warranty information.

We reserve the right to modify or amend specifications without prior notice.