	OLIREMARE		Model LOW4-4014-XL					
	LIQUID SEPARATION		Extra Area - Extra Low Energy, Excellent Productivity - Brackish Water E					
Туре		Configuration:				cer Material:		
		Spiral Wound	Composite Polyamide		Polypi	Polypropylene		
Specifications		Permeate		Nomina	Nominal Membrane			
		Flow:		Rejection:		Area:		
		700 gpd	99,0% nominal (98,0% minimum)			25ft ²		
		(2,65 m³/d)		((2,3m²)			
Test Con	ditions	Solution	Applied	Operating	Permeate	pН		
(After 30 min of		NaCl	Pressure:	Temperature:	Recovery:	Range:		
		500 ppm	100 psi	77 °F	10%	6,5 ÷ 7,0		
			(6,9 bar)	(25 °C)				

. .

-

1011

Di	mensions						
	A Total Length	B ATD Diameter		C Connection Diameter	D _F Core Tube Feed Side	D _C Extension Conc. Side	Weight
	14.0 inches <i>(355,6 mm)</i>	3.95 inches (100,3 mm)		0.75 inches <i>(19,1 mm)</i>	1.2 inches <i>(30,5 mm)</i>	1.2 inches <i>(30,5 mm)</i>	3 lbs (1,4 Kg)
		► D _F I	- A -		HD _C	P Permeate	
	F c	×			——————————————————————————————————————	F Feed	
	F c				Ic Cn	Cn Concentra	ite

Maximum Operating Limits								
Operating Pressure 7 Tape Wrapped	[emperature	Pressure Drop	Feed Flow	Chlorine Concentratio	Feedwater on SDI (15min)	Feedwater Turbidity		
300 psi <i>(20,7 bar)</i>	113 °F <i>(4</i> 5 ℃)	10 psi <i>(0,7 bar)</i>	12 gpm <i>(45,4 lpm)</i>	<0,1 ppm	5,0	1,0 NTU		
Other Operating Limits			Feedwate pH	r	Minimum ratio of concentra permeate flow for any eler			
			3,0 ÷ 10,0)	5:1			

The limitations shown in Operating Limits are for general use. The values may be more conservative for specific projects to ensure the best performance and longest life of the membrane.

Notice: Minimum permeate flow for individual elements 20 percent below listed flow. Elements are vacuum sealed in a polyethylene bag containing less than 1.0% sodium meta-bisulfite and 10% propylene glycol solution.

Guidelines: Permeate obtained from first hour of operation should be discarded.

Avoid static permeate-side backpressure at all times.

These membranes may be subject to drinking water application restrictions in some countries: please check the application status before use and sale.

For element loading use only glycerine to lubricate o-rings and brine seal.

The customer is fully responsible for the effects of incompatible chemicals on elements. The presence of free chlorine and other oxidizing agents will cause membrane failure, the damage is not covered under warranty.

Oltremare believes the information and data contained herein to be accurate and useful. The information and data are offered in good faith, but without guarantee, as conditions and methods of use of our products are beyond our control. Oltremare assumes no liability for results obtained or damages incurred through the application of the presented information and data. It is the user's responsibility to determine the appropriateness of Oltremare's products for the user's specific end uses.

No performance warranties are given; all implied warranties of merchantability or fitness for a particular purpose are expressly excluded. Consult factory for detailed warranty information.

We reserve the right to modify or amend specifications without prior notice.