	OLTR	EMARE	Model NANO7-2540				
	LIQUID SEPARATION		Ultra Low Energy, Excellent Ion Selective - Nanofiltration Element				
Туре		Configuration: Spiral Wound	M Co	embrane Polymer: mposite Polyamide	Brine Spacer Material: Polypropylene		
Specifications		Permeate Flow:		Stabilized Salt Rejection:	Nominal Membrane Area:		
		850 gpd (3,2 m³/d)		>97%	28ft <sup>2</sup> (2,6m <sup>2</sup> )		
Test Con (After 30 min of	nditions of operation)	Solution MgSO <sub>4</sub>	Applied Pressure:	Operating Temperature:	Permeate Recovery:	pH Range:	
		2000 ppm	70 psi (4,8 bar)	77 °F (25 °C)	10%	6,5 ÷ 7,0	

Dimensions					
A	B	C	D <sub>F</sub>	D <sub>C</sub>	Weight
Total	ATD	Connection	Core Tube	Extension	
Length	Diameter	Diameter	Feed Side	Conc. Side	
40.0 inches	2.4 inches	0.75 inches	1.2 inches	1.2 inches	4 lbs
<i>(1016 mm)</i>	<i>(61 mm)</i>	<i>(19,1 mm)</i>	<i>(30,5 mm)</i>	<i>(30,5 mm)</i>	(1,8 Kg)
F		· A	► P ► Cn	P Permeate F Feed Cn Concentra	ate

Maximum	Operating Li	mits					
Operatir Fiberglassed	ng Pressure Tape Wrapped	Temperature	Pressure Drop	Feed Flow	Chlorine Concentratio	Feedwater on SDI (15min)	Feedwater Turbidity
600 psi (41,4 bar)	300 psi (20,7 bar)	113 °F <i>(4</i> 5 ℃)	10 psi <i>(0,7 bar)</i>	6 gpm (23 lpm)	<0,1 ppm	5,0	1,0 NTU
Other Operating Limits				Feedwate pH	water Minimum ratio of concen H permeate flow for any el		oncentrate to any element
				3,0 ÷ 10,0	)	5:1	

The limitations shown in Operating Limits are for general use. The values may be more conservative for specific projects to ensure the best performance and longest life of the membrane.

Minimum permeate flow for individual elements 20 percent below listed flow. Elements are vacuum sealed in a polyethylene Notice: bag containing less than 1.0% sodium meta-bisulfite.

Guidelines: Permeate obtained from first hour of operation should be discarded.

Avoid static permeate-side backpressure at all times.

These membranes may be subject to drinking water application restrictions in some countries: please check the application status before use and sale.

For element loading use only silicon or glycerine to lubricate o-rings and brine seal.

The customer is fully responsible for the effects of incompatible chemicals on elements. The presence of free chlorine and other oxidizing agents will cause membrane failure, the damage is not covered under warranty. Oltremare believes the information and data contained herein to be accurate and useful. The information and data are offered in good

faith, but without guarantee, as conditions and methods of use of our products are beyond our control. Oltremare assumes no liability for results obtained or damages incurred through the application of the presented information and data. It is the user's responsibility to determine the appropriateness of Oltremare's products for the user's specific end uses.

No performance warranties are given; all implied warranties of merchantability or fitness for a particular purpose are expressly excluded. Consult factory for detailed warranty information.

We reserve the right to modify or amend specifications without prior notice.

LENNTECH info@lenntech.com Tel. +31-152-610-900 www.lenntech.com Fax. +31-152-616-289