| OLTREMARE         |
|-------------------|
| LIQUID SEPARATION |

## Model SEA2-2540

High Rejection, Excellent Productivity - Sea Water Element

| Туре   | Configuration:<br>Spiral Wound                          |  | embrane Polymer:<br>mposite Polyamide         |                              | cer Material:<br>opylene   |  |
|--|---|--|---|------------------------------|--|--|
| Specifications                                 | Permeate<br>Flow:<br>650 gpd<br>(2,5 m <sup>3</sup> /d) | Salt<br>Rejection:<br>99,4% nominal<br>(99,2% minimum) |   |                              | Nominal Membrane<br>Area:<br>28ft <sup>2</sup><br>(2,6m <sup>2</sup> ) |  |
| Test Conditions<br>(After 30 min of operation) | Solution<br>NaCl<br>32000 ppm                           | Applied<br>Pressure:<br>800 psi<br>(56 bar)            | Operating<br>Temperature:<br>77 °F<br>(25 °C) | Permeate<br>Recovery:<br>10% | pH<br>Range:<br>6,5 ÷ 7,0  |  |

| B<br>ATD<br>Diameter         | C<br>Connection<br>Diameter     | D <sub>F</sub><br>Core Tube I<br>Feed Side  | D <sub>C</sub><br>Extension<br>Conc. Side  | Weight   |
|------------------------------|---------------------------------|---|--|--|
| 2.4 inches<br><i>(61 mm)</i> | 0.75 inches<br><i>(19,1 mm)</i> | 1.2 inches<br>(30,5 mm)   | 1.2 inches<br><i>(30,5 mm)</i>   | 4 lbs<br>(1,8 Kg)  |
| D <sub>F</sub> H             | Α                               | ► D <sub>C</sub> ►  | P Permeate   |  |
|                              |                                 | <b>—————————————————————————————————————</b>  | F Feed<br>Cn Concentra   | ate  |
|                              | ATD<br>Diameter<br>2.4 inches   | ATD<br>DiameterConnection<br>Diameter2.4 inches<br>(61 mm)0.75 inches<br>(19,1 mm)A | ATD<br>DiameterConnection<br>DiameterCore Tube I<br>Feed Side2.4 inches<br>$(61 mm)$ 0.75 inches<br>$(19,1 mm)$ 1.2 inches<br>$(30,5 mm)$ $\Box_{F}$ A $\Box_{D_{C}}$ $\Box_{F}$ $H_{D_{C}}$ | ATD<br>DiameterConnection<br>DiameterCore Tube Extension<br>Feed Side2.4 inches<br>$(61 mm)$ 0.75 inches<br>$(19,1 mm)$ 1.2 inches<br>$(30,5 mm)$ $A \longrightarrow B_{F}^{I+}$ A $\longrightarrow B_{C}^{I+}$ P Permeate<br>Permeate |

| Maximum Operating Limits           |                           |                            |                   |                          |                            |  |  |  |  |
|------------------------------------|---------------------------|----------------------------|-------------------|--------------------------|----------------------------|--|--|--|--|
| Operating Pressure<br>Fiberglassed | Temperature               | Pressure<br>Drop           | Feed<br>Flow      | Chlorine<br>Concentratio | Feedwater<br>n SDI (15min) | Feedwater<br>Turbidity                                 |  |  |  |
| 1000 psi<br><i>(69 bar)</i>        | 113 °F<br><i>(4</i> 5 °C) | 10 psi<br><i>(0,7 bar)</i> | 6 gpm<br>(23 lpm) | <0,1 ppm                 | 5,0                        | 1,0 NTU  |  |  |  |
| Other Operating Limit              | s                         |                            |                   |                          |                            | mum ratio of concentrate to meate flow for any element |  |  |  |
|                                    |                           |                            | 3,0 ÷ 10,0        | )                        | 5:1                        |  |  |  |  |

The limitations shown in Operating Limits are for general use. The values may be more conservative for specific projects to ensure the best performance and longest life of the membrane.

Notice: Permeate flow for individual elements may vary + or -20 percent. Elements are vacuum sealed in a polyethylene bag containing less than 1.0% sodium meta-bisulfite.

Guidelines: Permeate obtained from first hour of operation should be discarded.

Avoid static permeate-side backpressure at all times.

These membranes may be subject to drinking water application restrictions in some countries: please check the application status before use and sale.

For element loading use only glycerine to lubricate o-rings and brine seal.

The customer is fully responsible for the effects of incompatible chemicals on elements. The presence of free chlorine and other oxidizing agents will cause membrane failure, the damage is not covered under warranty.

Oltremare believes the information and data contained herein to be accurate and useful. The information and data are offered in good faith, but without guarantee, as conditions and methods of use of our products are beyond our control. Oltremare assumes no liability for results obtained or damages incurred through the application of the presented information and data. It is the user's responsibility to determine the appropriateness of Oltremare's products for the user's specific end uses.

No performance warranties are given; all implied warranties of merchantability or fitness for a particular purpose are expressly excluded. Consult factory for detailed warranty information.

We reserve the right to modify or amend specifications without prior notice.