

Puorack® PPA510Plus

**Polystyrenic Macroporous Type II
Strong Base Anion Resin
Chloride form**

PRINCIPAL APPLICATIONS

- Demineralization - Industrial

ADVANTAGES

- High operating capacity
- High reversible sorptive capacity
- Excellent resistance to osmotic and physical shock

SYSTEMS

- Packed Bed Systems

TYPICAL PACKAGING

- 1 CF Sack
- 25 L Sack
- 5 CF Drum (Fiber)
- 1 M³ Supersack
- 42 CF Supersack

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Macroporous polystyrene crosslinked with divinylbenzene
Appearance	Spherical beads
Functional Group	Type II Quaternary Ammonium
Ionic Form	Cl ⁻
Total Capacity	1.15 eq/L (25.1 Kgr/ft ³) (Cl ⁻ form)
Moisture Retention	48 - 56 % (Cl ⁻ form)
Mean Diameter	750 ± 100 µm
Uniformity Coefficient	1.2 - 1.4
Reversible Swelling, Cl ⁻ → OH ⁻ (max.)	15 %
Specific Gravity	1.08
Shipping Weight (approx.)	680 - 710 g/L (42.5 - 44.4 lb/ft ³)
Temperature Limit	100 °C (212.0 °F) (Cl ⁻ form)
Temperature Limit	35 °C (95.0 °F) (OH ⁻ form)



LENNTECH

info@lennotech.com Tel. +31-152-610-900
www.lennotech.com Fax. +31-152-616-289

