

Product Data Sheet

PUROLITE® PPA500

Strong Base Anion Macroporous

LENNTECH

info@lenntech.com www.lenntech.com Tel. +31-15-261.09.00 Fax. +31-15-261.62.89

Macroporous Type I Strong Base Anion Exchange Resin

Puropack A500 is a specially produced, premium narrow size grading, macroporous type-I strong base anion exchange resin. Its macroporous structure offers excellent resistance to osmotic and physical shock, as well as a good reversible sorptive capacity for complex organic materials, such as the fulvic and humic acids which occur in many surface water supplies. It is one of a range of Puropack products manufactured for use in modern day water treatment applications. Puropack A500 is especially recommended for use in all counterflow demineralization systems, including the Puropack system. It has a specially tailored size grading which provides for economical regeneration by counterflow techniques. Puropack is a maximum performance packed bed system which provides a combination of superior engineering principles and improved resins that together optimize water treatment plant performance. For more information please refer to the Puropack Manual or your local Purolite Sales Office.

Basic Features:

Application	Demineralization - Narrow Size Grading
Polymer Structure	Macroporous polystyrene crosslinked with divinylbenzene
Appearance	Spherical beads
Functional Group	Type 1 Quaternary Ammonium
lonic form as shipped	CI

Typical Physical and Chemical Characteristics:

Total Capacity (min.)	Cl	1.15 eq/l
Total Capacity (min.)	Cl	25.11 kGr/ft ³
Moisture Retention	Cl	53-58 %
Mean Size Typical		0.60-0.70 mm
Uniformity Coefficient (max.)		1.20
Reversible Swelling (max.)	$\text{CI}^{\text{-}} \rightarrow \text{OH}^{\text{-}}$	15 %
Specific Gravity		1.08 g/ml
Shipping Weight (approx.)		670-690 g/l
Temp Limit	OH	65 °C
Temp Limit	OH	150 °F
Temp Limit	Cl	100 °C
Temp Limit	Cl	212 °F
pH Limits		0-14 (Stability)



Product Data Sheet

PUROLITE® PPA500
Strong Base Anion Macroporous

pH Limits

0-11 (Operating)

 H^+

LENNTECH

info@lenntech.com www.lenntech.com Tel. +31-15-261.09.00 Fax. +31-15-261.62.89