

Puropack® PPC150H

Polystyrenic Macroporous Strong
Acid Cation Resin Hydrogen
form, Packed Bed Grade

PRINCIPAL APPLICATIONS

- Demineralization

SYSTEMS

- Counterflow
- Packed Bed Systems

TYPICAL PACKAGING

- 1 CF Sack
- 25 L Sack
- 5 CF Drum (Fiber)
- 1 M³ Supersack
- 42 CF Supersack

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Macroporous polystyrene crosslinked with divinylbenzene
Appearance	Spherical beads
Functional Group	Sulfonic Acid
Ionic Form	H ⁺
Total Capacity	1.8 eq/L (39.3 Kgr/ft³) (Na ⁺ form)
Moisture Retention	54 - 59 % (H ⁺ form)
Mean Diameter	750 ± 100 µm
Uniformity Coefficient	1.2 - 1.4
Reversible Swelling, Na ⁺ → H ⁺ (max.)	4 %
Specific Gravity	1.18
Shipping Weight (approx.)	730 - 770 g/L (45.6 - 48.1 lb/ft³)
Temperature Limit	120 °C (248.0 °F) (H ⁺ form)
Temperature Limit	140 °C (284.0 °F) (Na ⁺ form)



LENNTECH

info@lennotech.com Tel. +31-152-610-900
www.lennotech.com Fax. +31-152-616-289

